

IN THE CLAIMS

1. (CURRENTLY AMENDED) A method to solve via poisoning for insulative porous low-k materials comprising the steps of:

providing a substrate having a first and a second insulative layers separated from each other by an intervening etch-stop layer formed therein said substrate;

forming a hole opening in said first and second insulative layers, including said intervening etch-stop layer;

forming a low-k protection layer over said second insulating layer, including in said hole opening, wherein said low-k protection layer prevents outgassing from said first and second insulative layers;

forming a trench opening over said hole opening to form a dual damascene structure, said hole opening containing said low-k protection layer;

forming a barrier layer on the vertical walls of said trench opening and on said low-k protection layer on the vertical walls of said hole opening;

forming a metal layer on said barrier layer in said dual damascene structure; and

performing chemical mechanical polishing (CMP), to complete the forming of

TS00-563

said dual damascene structure.

2. (ORIGINAL) The method of claim 1, wherein said first insulative layer is a low-k dielectric having a dielectric constant between about 2.0 to 3.0.

3. (ORIGINAL) The method of claim 1, wherein said first insulative layer has a thickness between about 2000 to 100000 Å.

4. (ORIGINAL) The method of claim 1, wherein said intervening etch-stop layer is silicon nitride.

5. (ORIGINAL) The method of claim 1, wherein said intervening etch-stop layer has a thickness between about 50 to 1000 Å.

6. (ORIGINAL) The method of claim 1, wherein said second insulative layer is a low-k dielectric having a dielectric constant between about 2.0 to 3.0.

7. (ORIGINAL) The method of claim 1, wherein said second insulative layer has a thickness between about 2000 to 100000 Å.

8. (PREVIOUSLY PRESENTED) The method of claim 1, wherein said low-k protection layer comprises SiO₂, SiN, SiC or SiNC.

TS00-563

9. (ORIGINAL) The method of claim 1, wherein said low-k protection layer has a thickness between about 20 to 1000 Å.

10. (PREVIOUSLY PRESENTED) The method of claim 1, wherein said barrier layer material is selected from the group comprising Ta, Ti, TaN, TiSiN, TaSiN, or WN.

11. (ORIGINAL) The method of claim 1, wherein said barrier layer has a thickness between about 30 to 500 Å.

12. (ORIGINAL) The method of claim 1, wherein said metal comprises copper.

13. (CURRENTLY AMENDED) A method to solve via poisoning for insulative porous low-k materials in a dual damascene structure comprising the steps of:

providing a substrate having a passivation layer formed over a first metal layer formed on said substrate;

forming a first insulative layer over said substrate;

forming an etch-stop layer over said first insulative layer;

forming a second insulative layer over said etch-stop layer;

forming a first photoresist layer over said second insulative layer and patterning said photoresist to form a first photoresist mask having a hole pattern;

etching said first and second insulative layers, including said etch-stop layer through said hole pattern to form a hole opening in said first and second insulative layers and reaching said passivation layer;

removing said first photoresist mask ~~from said second insulative layer~~;

~~forming a low-k protection layer over said substrate on said second insulative layer, including in said hole opening;~~

forming a low-k protection layer in said hole opening in said first and second insulative layers, including over said substrate;

forming a second photoresist layer over said substrate, including over said hole opening having said low-k protection layer and patterning said second photoresist to form a second photoresist mask having a trench pattern; .

etching said second insulative layer through said trench pattern in said second photoresist mask to form a trench in said second insulative layer, thus completing the forming of said dual damascene structure in said substrate;

TS00-563

removing said second photoresist mask;

removing said low-k protection layer from over said substrate and from the bottom of said hole opening and thereby exposing underlying said passivation layer while leaving said low-k protection layer on the vertical sides of said hole opening;

removing said passivation layer from said bottom of said hole opening, thereby exposing underlying said first metal layer;

forming a barrier layer over said substrate, including in said dual damascene structure, wherein said barrier layer conforms to said low-k protective layer in said hole opening and conforms to said trench in said second insulative layer;

depositing a second metal over said barrier layer in said dual damascene structure; and

performing chemical mechanical polishing (CMP) to complete the forming of said dual damascene structure.

14. (ORIGINAL) The method of claim 13, wherein said substrate is silicon.

TS00-563

15. (ORIGINAL) The method of claim 13, wherein said passivation layer comprises silicon nitride (SiN).

16. (ORIGINAL) The method of claim 13, wherein said passivation layer has a thickness between about 30 to 1000 Å.

17. (ORIGINAL) The method of claim 13, wherein said first insulative layer is a low-k dielectric having a dielectric constant between about 2.0 to 3.0.

18. (ORIGINAL) The method of claim 13, wherein said first insulative layer has a thickness between about 2000 to 100000 Å.

19. (ORIGINAL) The method of claim 13, wherein said intervening etch-stop layer is silicon nitride.

20. (ORIGINAL) The method of claim 13, wherein said intervening etch-stop layer has a thickness between about 30 to 1000 Å.

21. (ORIGINAL) The method of claim 13, wherein said second insulative layer is a low-k dielectric having a dielectric constant between about 2.0 to 3.0.

22. (ORIGINAL) The method of claim 13, wherein said second insulative layer has a thickness between about 2000 to 100000 Å.

23. (ORIGINAL) The method of claim 13, wherein said etching said first and second insulative layers is accomplished with a recipe comprising C_2F_6 , C_4F_3 , Ar, N_2 and O_2 .

24. (ORIGINAL) The method of claim 13, wherein said etching said etch-stop layer is accomplished with a recipe comprising C_2F_6 , C_4F_3 , Ar, N_2 and O_2

25. (PREVIOUSLY PRESENTED) The method of claim 13, wherein said low-k protection layer material is selected from the group comprising SiO_2 , SiN, SiCN or SiC.

26. (ORIGINAL) The method of claim 13, wherein said low-k protection layer has a thickness between about 30 to 1000 Å.

27. (ORIGINAL) The method of claim 13, wherein said removing said low-k protection layer is accomplished with a recipe comprising C_2F_6 , C_4F_3 , Ar, N_2 and O_2 .

28. (PREVIOUSLY PRESENTED) The method of claim 13, wherein said barrier layer material is selected from the group comprising Ta, Ti, TaN, TiSiN, TaSiN, or WN.

TS00-563

29. (ORIGINAL) The method of claim 13, wherein said barrier layer has a thickness between about 30 to 500 Å.

30. (ORIGINAL) The method of claim 13, wherein said second metal comprises copper.